


ELMORUSTICAL







AVERAGE HIDE SIZE

5 sqm

THICKNESS / WEIGHT

1.3 - 1.5 mm / 980gsm

LEATHER TYPE

Pure Aniline

COLOURFASTNESS TO-AND-FRO RUBBING EN ISO 11640 + 11641

Dry 4 Wet 4 Perspiration 4

LIGHTFASTNESS EN ISO 105-B02 2

pH AND ∆pH EN ISO 4045 $pH > 3.2 \Delta pH \le 0.7$

TEAR STRENGTH EN ISO 3377-1

> 20 N

FIRE RATINGS AS/N7S 15303

Ignitability 14
Spread of Flame 0
Heat Evolved 2
Smoke Developed 4

AS/NZS 3837

BCA Group 1

Av. Specific Extinction Area 186.7m2/kg

Available on request

Cal 117, EN 1021-1+2, FAR 25.853(a), IMO A.652(16), ISO 8191: 1+2

EMBOSSED ELMODESIGN

Available in Pique, Herringbone, Wicker Weave, Basket Weave, Small Basket Weave, Ferrari + Lamborghini. Refer to Embossed Elmodesign brochure

PLEASE NOTE

Only the best raw hides are used for Pure-Aniline leathers. The natural characteristics such as insect bites, fat wrinkles, growth marks and healed scars can still be visible, a sign of a superior leather with individuality. Pure-Aniline leathers do not have any protective coating or pigment on the surface and are therefore more susceptible to fading from sunlight exposure. Care should be taken in high traffic areas where food and drink spillages could stain the leather. Results from performance tests are guidelines only.

CARE

Leather Care for Aniline Leathers is available from our website

ENVIRONMENT

- Leather is an agricultural by-product
- Reduced energy consumption (5%), reuse / recycling of waste (95%), no hazardous substances are used
- Produced at a tannery with an ISO 14001 certified Environmental Management System
- Certified as low-VOC
- Reusable

GREEN STAR

- ELMORUSTICAL can contribute low VOC points
- ELMORUSTICAL can be used on white furniture certified to Ecospecifier, AFRDI, ECNZ and GECA
- The Green Star Rating Tool states "Where at least 90% of an item's mass is certified to a GBCA recognised standard, the item can be entered as a certified product at Level A, B or C." Therefore any leather can be used as leathers are almost always under 10% by weight of a furniture item

LEED

ELMORUSTICAL can contribute low VOC points

WELL

- ELMORUSTICAL can contribute to Low VOC / VOC Reduction
- Toxic Material Reduction: ELMORUSTICAL is free of PFCs, flame retardants, phthalates and urea formaldehyde

SEATING COMFORT RATING



A rating to determine a leather's seating comfort based upon the leather's ability to breathe and absorb moisture.

Tested to ASTM E 96 M-05.

ELMORUSTICAL achieves an Excellent Seating Comfort rating.

